



ANTI-STATIC POLYCARBONATE PC-350™

Properties - Mechanical	Test Methods	Units	Values
Specific gravity	ASTM D792	-	1.2
Tensile strength			
- Ultimate	ASTM D638	psi	9,500
- Elongation	ASTM D638	%	100
Tensile modulus	ASTM D638	psi	340,000
Flexural strength	ASTM D790	psi	13,500
Flexural modulus	ASTM D790	psi	340,000
Compressive strength	ASTM D695	psi	12,500
Izod impact strength	ASTM D256	ft-lb / inch of notch	16
Thermal Properties			
Deflection temperature (264 psi load)	ASTM D648	°F	270
Service temperature	ASTM 1525	°F	310
Maximum continuous service temperature	/	°F	180
Coefficient of thermal expansion	ASTM D696	in / in / °F	3.5 x 10 ⁻⁵
Coefficient of thermal conductivity	Ceneco-Fitch	BTU•in/hr•ft ² •°F	1.35
Flammability			
Horizontal burn (flame spread)	ASTM D635	in/min	less than 1.0
UL94 rating of the uncoated substrate	UL 94	UL 94	V-2<6mm≥V-0
Optical Properties			
3mm Transparent clear transmittance - total	ASTM D1003	%	75
Haze	ASTM D1003	%	less than 5.0
Electrical Properties			
Surface resistivity	ASTM D257	Ohms/sq	10 ⁶ - 10 ⁸
Surface resistance	EOS/ESD S11.11	Ohms	10 ⁵ - 10 ⁷
Electrostatic Decay	FTS 101C Method 4046.1	sec	less than 0.05

PC-350™ is a trademark of SciCron Technologies.

For latest datasheets, visit our website:

aiplastics.com

While the information on this data sheet is believed to be correct at the time of publication, it is the customer's responsibility to ensure the correct use and application of this product. The buyer undertakes all liability in respect of the application, processing or use of this information or product, whose quality and other properties he shall verify, or any consequence thereof.